

# 840R

## VOC EPOXY PRIMER-SURFACER



### PRODUCT DESCRIPTION

VOC Epoxy Primer-Surfacer 840R Off White is a VOC-compliant, versatile 2K chromate-free epoxy primer-surfacer. It offers outstanding corrosion resistance and adhesion, and meets homologation requirements of certain car manufacturers.

**Not** for use under Cromax Pro Basecoat

**Robust primer-surfacer**

### FEATURES

- 01 Suitable for use as a sanding and as a non-sanding primer-surfacer.
- 02 Suitable for use on rough substrates such as grit-blasted metals.
- 03 Recommended as a first coat over bare metals.
- 04 Single step quality repair primer-surfacer, eliminated the need for a wash primer.
- 05 Provides excellent adhesion to properly treated metal substrates.
- 06 Suitable for tinting with AM Centari MasterTints, up to maximum 10% by weight.
- 07 Provides very good filling properties.
- 08 Has very good corrosion and chemical resistance.

# TECHNICAL DATA SHEET




**840R**

## VOC EPOXY PRIMER-SURFACER

### Product preparation - application STANDARD NON-SANDING



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Bare steel sanded and cleaned  
Galvanised steel or aluminium, sanded and cleaned  
Old or original paintwork well sanded and cleaned  
OEM Primer (e-coat), finely sanded or unsanded and thoroughly cleaned. Remark: due to the wide variety of electrocoats present on the market, its quality can differ a lot. For this reason preferably scuff sand the e-coat  
Surfaces pretreated with 2K polyester products and then finely sanded and cleaned  
Glass fibre reinforced polyester substrates, free of release agents, sanded and cleaned.



M-6152 / M-6153

	VS2	VS3	VS4	VS5
<b>840R</b>	100	100	100	100
<b>AM5</b>	-	1.5	5	10
<b>Standard</b>				
	Volume		Weight	
<b>840R</b>	4		100	
<b>845R</b>	1		14	
<b>XB387</b>	1.5		20	



Pot life at 20°C: 8 hr



	Spray nozzle	Spray pressure	
<b>Compliant</b>	1.3 - 1.5 mm	1.5 - 2 bar	inlet pressure
<b>HVLP</b>	1.3 - 1.5 mm	0.7 bar	atomisation pressure

see manufacturer's instructions



	Primer	Primer-surfacer
1 coat	final flash-off: 30 min - 2 hr	1 - 2 coats with intermediate flash-off: 5 min - 10 min final flash-off: 1 hr - 2 hr



	Primer	Primer-surfacer
2K Surfacer		Centari 2K Topcoats Centari Basecoats

VOC compliant

2004/42/IIB(c)(540) 540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

# TECHNICAL DATA SHEET




**840R**

## VOC EPOXY PRIMER-SURFACER

### Product preparation - application STANDARD SANDING



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Bare steel sanded and cleaned  
Galvanised steel or aluminium, sanded and cleaned  
Old or original paintwork well sanded and cleaned  
OEM Primer (e-coat), finely sanded or unsanded and thoroughly cleaned. Remark: due to the wide variety of electrocoats present on the market, its quality can differ a lot. For this reason preferably scuff sand the e-coat  
Surfaces pretreated with 2K polyester products and then finely sanded and cleaned  
Glass fibre reinforced polyester substrates, free of release agents, sanded and cleaned.



M-6152 / M-6153

	VS2	VS3	VS4	VS5
<b>840R</b>	100	100	100	100
<b>AM5</b>	-	1.5	5	10
		Standard		
		Volume	Weight	
<b>840R</b>		3	100	
<b>845R</b>		1	18	
<b>AU370 / XB387</b>		1	18	



Pot life at 20°C: 8 hr



	Spray nozzle	Spray pressure	
<b>Compliant</b>	1.3 - 1.5 mm	1.5 - 2 bar	inlet pressure
<b>HVLP</b>	1.3 - 1.5 mm	0.7 bar	atomisation pressure

see manufacturer's instructions



2 - 3 coats

with intermediate flash-off: 5 min - 10 min  
before bake: 5 min - 10 min



	845R / AU370	845R / XB383
<b>20 °C</b>	12 hr - 16 hr	12 hr - 16 hr
<b>60 - 65 °C</b>	35 min	35 min



Guideline for short wave IR equipment  
Half power: 5 min  
Full power: 12 - 15 min



P400 - P500



Centari 2K Topcoats  
Centari Basecoats

VOC compliant

2004/42/IIB(c)(540) 540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

# TECHNICAL DATA SHEET



**840R**

## VOC EPOXY PRIMER-SURFACER


### Products

840R VOC Epoxy Primer-Surfacer  
AM5 Centari® MasterTint® Jet Black


845R Epoxy Activator

AU370 Imron® 700 Polyurethane Thinner  
XB383 Standard Thinner  
XB387 HI-Temp Thinner

### Product mix



Mixing ratios with special agents are available in the productmix table on ChromaWeb and in the specific TDS.



DIN 4: 16 - 19 s at 20°C



60 - 110 µm sanding  
20 - 30 µm non-sanding



Clean after use with a suitable solventbased guncleaner.

### Remarks

- Material has to be at room temperature (18-25°C) before use.
- Allow additional time for preheating up to panel temperature.
- Surplus ready for use material should not be returned to original can.
- Can not be applied over acid containing primers.
- Polyester putties can be applied over cured and sanded epoxy primer-surfacers.
- 840R can be applied by brush if no reducer is added to the activated material.
- Do not use under Cromax Pro Basecoats.

# TECHNICAL DATA SHEET

**840R**



## VOC EPOXY PRIMER-SURFACER

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Cromax product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Cromax product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.