

Standox Etching Adhesion Primer U3100

Standox Etching Adhesion Primer U3100 is a versatile, chromate-free 2K wash primer for steel, aluminium and galvanised substrates. It is mixed in a 1:1 ratio with Standox Etching Adhesion Activator U3110. It is also available in a professional spray can for quick repairs of small areas.

- Transparent 2K acid primer.
- Superior adhesion.
- Outstanding corrosion protection.
- Part of refinish systems with OEM approval.

Versatile adhesion primer.




Standex Etching Adhesion Primer U3100


Product preparation - application STANDARD



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Bare steel sanded and cleaned
Galvanised steel or soft aluminium sanded and cleaned.
OEM Primer (e-coat), sanded and cleaned
Surfaces pretreated with 2K polyester products and then finely sanded and cleaned
Old or original paintwork well sanded and cleaned



Primer		Activator	
Volume	Weight	Volume	Weight
100 %	100	100 %	90
U3100		U3110	



Pot life at 20°C: 8 hr




	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.4 mm	1.8 - 2 bar	inlet pressure
HVLP	1.3 - 1.5 mm	0.7 bar	atomisation pressure
see manufacturer's instructions			



1 - 2 coats
with intermediate flash-off: 5 min - 10 min
final flash-off: 30 min



	U3110
20 °C	30 min



2K Filler

VOC compliant

2004/42/IIB(c)(780) 780: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 780 g/l of VOC. The VOC content of this product in ready to use form is maximum 780 g/l.


Standex Etching Adhesion Primer U3100

Products


Standex Etching Adhesion Primer U3100

Standex Etching Adhesion Activator U3110

Product mix



Mixing ratios with special agents are available in the productmix table on Standwin IQ and in the specific TDS.



DIN 4: 16 - 18 s at 20°C



8 - 10 µm



Clean after use with a suitable solventbased guncleaner.

Remarks

- Material has to be at room temperature (18-25°C) before use.
- Surplus ready for use material should not be returned to original can.
- Do not recoat with polyester-, epoxy- or waterborne products.
- Only use plastic or inner coated metal cans.
- Maximum time before overcoating is 48 hours.
- Not suitable for application on thermoplastic paintwork.

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Standox product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Standox product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

