

Standox Performance Blend 5730

Standox Performance Blend 5730 is a blending thinner for fading out on old and original paintworks. It is ideally suited for blending/fading out when using Standocryl new generation clears.



- For seamless edge zones in blending areas.
- Excellent resolving properties of old and original paintwork.
- Particularly suited for Standocryl new generation clears.
- Low polishing effort.

Blending thinner for Standocryl new generation clears.




Standex Performance Blend 5730

Product preparation - application STANDARD



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Can be used with:

2K Hardened	Standocryl VOC Performance Pro Clear K9590
-------------	--------------------------------------------

2K Hardened	Standocryl VOC Xtreme Clear K9580
-------------	-----------------------------------

2K Hardened	Standocryl VOC Xtreme Plus Clear K9600
-------------	----------------------------------------

For recommended instructions see following pages.



Not applicable

VOC compliant

This product mix is not VOC compliant.

Standex Performance Blend 5730

Product preparation - application Spray can



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.




Can be used with:

2K Hardened	Standocryl VOC Performance Pro Clear K9590
-------------	--------------------------------------------

2K Hardened	Standocryl VOC Xtreme Clear K9580
-------------	-----------------------------------

2K Hardened	Standocryl VOC Xtreme Plus Clear K9600
-------------	----------------------------------------

For recommended instructions see following pages.



Not applicable

VOC compliant

2004/42/IIB(e)(840) 810: The EU limit value for this product (product category: IIB(e)) in ready to use form is maximum 840 g/l of VOC. The VOC content of this product in ready to use form is maximum 810 g/l.

Standex Performance Blend 5730


Blend-in method for Standocryl VOC Clears



Polish the fade-out zone with a coarse polish compound and wipe off all residues. Sand the transition to damage area with e.g. 3M Trizact P3000 Fine Finishing Disc or similar abrasives from other suppliers. Clean the sanded and polished area sufficiently with Standox Precleaner 6800.



Mix Standocryl VOC Performance Pro Clear K9590, Standocryl VOC Xtreme Clear K9580 or Standocryl VOC Xtreme Plus Clear K9600 according to the TDS. Overcoat the appropriate Standox basecoat quality with ready-to-spray Standocryl VOC Performance Pro Clear K9590, Standocryl VOC Xtreme Clear K9580 or Standocryl VOC Xtreme Plus Clear K9600. Fade out the clear in staggered coats with reduced pressure onto the sanded area and till the edge of the polished area.



Apply the pure Performance Blend 5730 in thin coats to the polished fade-out area (reduce pressure when using spray gun). Dissolve the overspray and smooth the transition of the clear. Dry according to the TDS of the respective clear. Additional IR drying of the fade-out area may reduce the risk of the edge rolling back when polished.



If required, lightly sand the transition zone after drying and cooling depending on the finish to be achieved e.g. with 3M Trizact P3000 or similar.

Polish using a rotary polish machine. Make sure to control contact pressure and direction of rotation from the closed topcoat film to the fade-out area.

Standex Performance Blend 5730

Products

Standex Performance Blend 5730



Clean after use with a suitable solventbased guncleaner.

Remarks

- Performance Blend 5730 to be used with Standocryl VOC Performance Pro Clear K9590, VOC Xtreme Clear K9580 or VOC Xtreme Plus Clear K9600 only.
-

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Standox product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Standox product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

