

# Standox Spray Filler U1100

**Standox Polyester Spray Filler U1100 is a thick film spray putty that replaces putty work and can be used as a sprayable fine putty.**

- Spray filler.
- Easy to sand.
- Pore-free finish.
- Can be used as a fine putty.




# Standex Spray Filler U1100

## Product preparation - application STANDARD



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Surfaces pretreated with 2K polyester products and then finely sanded and cleaned.  
 Glass fibre reinforced polyester substrates, free of release agents, sanded and cleaned.  
 Old or original paintwork well sanded and cleaned.  
 Fully cured 2K Fillers or 2K Epoxy Primer-surfacer sanded and cleaned  
 OEM Primer (e-coat), sanded and cleaned.  
 Steel, galvanised steel and light aluminium, sanded and cleaned, coated with primer and overcoated with 2K Filler



Stopper		Hardener		Thinner	
Volume	Weight	Volume	Weight	Volume	Weight
100	100	5	3.6	0 - 5%	0 - 5%
U1100		U1110 / AXT560		11008	



Pot life at 20°C: 20 min - 30 min



	Spray nozzle	Spray pressure	
Compliant	2 - 2.5	2 - 3 bar	inlet pressure

see manufacturer's instructions



1 - 5 coats  
 without intermediate flash-off  
 before bake: 5 min - 10 min



	U1110 / AXT560
20 °C	2 hr
60 - 65 °C	30 min - 35 min



Guideline for short wave IR equipment  
 Half power: 10 - 12 min



Coarse sand: P120 - P220  
 Final sand: P240 - P360



Primer  
 Primer-Surfacer  
 Filler

VOC compliant

2004/42/IIB(b)(250) 250: The EU limit value for this product (product category: IIB(b)) in ready to use form is maximum 250 g/l of VOC. The VOC content of this product in ready to use form is maximum 250 g/l.

# Standex Spray Filler U1100

## Products

Standex Spray Filler U1100

AXT560 Hardener for 2K Spray Putty  
Standex PE Hardener U1110

Standex Thinner Polyester 11008

500 - 600 µm film thicknesses up to 1000µm are possible



Clean after use with a suitable solventbased guncleaner.

## Remarks

- Material has to be at room temperature (18-25°C) before use.
- Do not apply over 1K primer, etch primer or thermoplastic acrylic finishes.
- Do not wet sand.
- Polyester materials have a limited shelf life. Store in a cool place, and use within 12 months for best results.

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Standox product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Standox product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

