

Standoflex Plastic Primer U3060



Standoflex Plastic Primer U3060 is a 1K primer for tri-coat application on plastics. It is easy to use and adheres to most commonly used exterior plastic car parts.

- Easy to use.
- Adheres to all exterior plastic car parts.
- 1K Primer for three-stage plastic refinishing.

1K primer for painting plastic parts.




The Art of Refinishing.

Standoflex Plastic Primer U3060


Product preparation - application STANDARD



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



New exterior common plastic car parts, tempering 60 min. 60-65°C / first cleaning use a pad ultrafine soaked in plastic cleaner / final cleaning use a cloth moistened with plastic cleaner.
Repairs to exterior common plastic car parts, sanded and cleaned.



Primer	
Volume	Weight
100	100
U3060	



Not applicable




	Spray nozzle	Spray pressure	
Compliant	1.2 - 1.3	1.5 - 2 bar	inlet pressure
HVLP	1.3 - 1.4	0.7 bar	atomisation pressure
see manufacturer's instructions			



1 normal coat	final flash-off: 10 min
---------------	-------------------------



20 °C	10 min
-------	--------



Appropriate Filler
Stopper

VOC compliant


This product mix is out of scope for VOC directive

Standoflex Plastic Primer U3060


Products

Standoflex Plastic Primer U3060

Product mix



Mixing ratios with special agents are available in the productmix table on Standowin IQ and in the specific TDS.



1 - 2 μm



Clean after use with a suitable solventbased guncleaner.

Remarks

- Material has to be at room temperature (18-25°C) before use.
- Shake before use.
- Coated plastic parts should not be washed with a high-pressure jet cleaner within the first six weeks. After this period, the nozzle must be held at a distance of no less than 30cm from the object.

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Standox product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Standox product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

