

# Standocryl Standard Clear K9440



**Standocryl Standard Clear K9440 is a versatile 2K clearcoat for partial and full repairs.**

- Universal 2K MS clearcoat.
- Offers wide application window.
- Can be applied over Standox waterborne basecoats.
- Excellent durability, good hold-out and gloss retention.
- Fast throughput, helps increase productivity

**All rounder.**




**The Art of Refinishing.**

# Standocryl 2K Standard Clear K9440

## Product preparation - application STANDARD - VOC



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Standoblue Basecoat: Surfaces must be dried / flashed-off in accordance with TDS before application.



Clear		Hardener	
Volume	Weight	Volume	Weight
4	100	1	27
K9440		VOC 10-20 VOC 20-25 VOC 25-30 VOC 30-40	



Pot life at 20°C: 2 - 3hr



	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.4 mm	1.8 - 2.2 bar	inlet pressure
HVLP	1.3 - 1.4 mm	0.7 bar	atomisation pressure
see manufacturer's instructions			



2 coats intermediate and final flash-off: 5 min



	VOC10-20/20-25/25-30/30-40
20 °C	Overnight
60 - 65 °C	20 min - 40 min



Guideline for short wave IR equipment  
Half power: 5 min  
Full power: 15 - 20min

VOC compliant


This product mix is not VOC compliant.

# Standocryl 2K Standard Clear K9440

## Product preparation - application STANDARD - HS



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Standoblue Basecoat: Surfaces must be dried / flashed-off in accordance with TDS before application.



Clear		Hardener	
Volume	Weight	Volume	Weight
33	100	1	3734
K9440		HS 5-15 HS 15-25 HS 20-30 HS 25-40	



Pot life at 20°C: 3 - 4hr



	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.4 mm	1.8 - 2.2 bar	inlet pressure
HVLP	1.3 - 1.4 mm	0.7 bar	atomisation pressure
see manufacturer's instructions			



2 coats intermediate and final flash-off: 5 min



	HS5-15/HS15-25/HS20-30/HS25-40
20 °C	Overnight
60 - 65 °C	20 min - 40 min



Guideline for short wave IR equipment  
 Half power: 5 min  
 Full power: 15 - 20min

VOC compliant

This product mix is not VOC compliant.

# Standocryl Standard Clear K9440

## Products

---

Standocryl Standard Clear K9440

---

Stadox Hardener VOC 10-20  
Stadox Hardener VOC 20-25  
Stadox Hardener VOC 25-30  
Stadox Hardener VOC 30-40


Stadox Hardener HS 15-25  
Stadox Hardener HS 20-30  
Stadox Hardener HS 25-40  
Stadox Hardener HS 5-15

---



# Standocryl Standard Clear K9440


## Product mix



Mixing ratios with special agents are available in the product mix table on Standowin IQ and in the specific TDS.

The choice of Hardener should be made according to application temperature and size of repair.


HS 5-15	Accelerated fast hardener suitable for Micro and Spot repairs. Recommended for cooler application conditions. Suitable for Standox Fillers for air drying at lower temperatures.
HS 15-20	Medium hardener suitable for panel and multi panel repairs. Recommended for application temperature of 15-25°C.
HS 20-30	Medium-slow hardener suitable for medium to large size repairs. Recommended also for warm conditions e.g. 20-30°C.
HS 25-40	Non-accelerated slow hardener suitable for medium to large size repairs. Recommended for use in hot climates e.g. 25-40°C.
VOC 10-20	Accelerated fast hardener suitable for Micro Repair, spot and panel repairs. Recommended for cooler application conditions e.g. 10-20°C.
VOC 20-25	Medium hardener suitable for panel and multi panel repairs. Recommended for application temperature of 20-25°C.
VOC 25-30	Medium-slow hardener suitable for medium to large size repairs. Recommended also for warm conditions e.g. 25-30°C.
VOC 30-40	Non-accelerated slow hardener suitable for medium to large size repairs. Recommended for use in hot climates e.g. 30-40°C.



DIN 4: 16 - 18s at 20°C



45 - 65µm



Standocryl Standard Clear K9440 can be recoated within 24 hours, without intermediate sanding



Clean after use with a suitable solventbased guncleaner.

# Standocryl Standard Clear K9440

---

## Remarks

---

- Material has to be at room temperature (18-25°C) before use.
  - Allow additional time for preheating up to panel temperature.
  - Surplus ready for use material should not be returned to original can.
  - Close can of hardener tightly immediately after use, as this product will react with humid air and water and lose its hardening effect.
  - 10 - 15% Standox Plasticiser 5660 can be added to the Clearcoat. Hardener and thinner ratios are changed to 3:1 with VOC hardener + 5% thinner & 2:1 with HS hardener + 5% thinner. Drying times will be longer.
- 

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Standox product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Standox product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.

